




# tesa® 66985

## Product Information



250µm double sided black chemical resistant PE foam tape

## Product Description

tesa® 66985 is a black double-sided tape consisting of a shock absorbing PE-foam backing equipped with chemical resistance adhesive.

tesa® 66985 features:

- Excellent chemical resistance
- Outstanding shock performance
- Good rework ability
- Waterproofness

## Application Fields

- Smart Phone & Feature Phone: Lens mounting & touch panel mounting
- Tablet & Touch laptop: Lens mounting & touch panel mounting
- Smart watch: Lens mounting & touch panel mounting
- Smart TV: Lens mounting & frame mounting
- Battery mounting

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- |                    |                   |                   |        |
|--------------------|-------------------|-------------------|--------|
| • Backing material | PE foam           | • Total thickness | 250 µm |
| • Type of adhesive | tackified acrylic | • Color           | black  |

## Properties/Performance Values

- |                          |           |                                   |      |
|--------------------------|-----------|-----------------------------------|------|
| • Elongation at break    | 220 %     | • Humidity resistance             | good |
| • Tensile strength       | 10.7 N/cm | • Static shear resistance at 23°C | good |
| • Ageing resistance (UV) | good      | • Static shear resistance at 40°C | good |

## Adhesion to Values

- |                         |           |                         |           |
|-------------------------|-----------|-------------------------|-----------|
| • ABS (initial)         | 7.2 N/cm  | • PC (after 14 days)    | 15.2 N/cm |
| • ABS (after 14 days)   | 13.4 N/cm | • PMMA (initial)        | 8.5 N/cm  |
| • Glass (initial)       | 8 N/cm    | • PMMA (after 14 days)  | 13.4 N/cm |
| • Glass (after 14 days) | 8.2 N/cm  | • Steel (initial)       | 6.8 N/cm  |
| • PC (initial)          | 8.5 N/cm  | • Steel (after 14 days) | 7.2 N/cm  |

For latest information on this product please visit <http://l.tesa.com/?ip=66985>



# tesa<sup>®</sup> 66985

## Product Information

### Additional Information

Liner: PV80 transparent PET-film (75µm)

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=66985>