



**Product Information** 



#### 1600µm double sided PE foam tape

#### **Product Description**

tesa® 64962 is a double sided PE foam tape. The tape is equipped with a synthetic rubber adhesive.

tesa® 64962 features:

- Thickness: 1600μm
- Excellent immediate bonding strength
- High bonding strength even on low surface energy substrates
- Highly conformable foam backing provides high bonding strength on rough or uneven surfaces
- Multi-purpose tape suitable for hand or automatic application

#### **Application Fields**

- · Bonding of trims and profiles (plastic extrusions)
- \* Mounting of shelf edge labelling systems
- \* Fixing of cable channels
- \* Construction of POS-displays
- \* Mounting of indoor signs
- \* Assembly aid, pre-fixation

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

- Type of liner
- Backing material
- Type of adhesive
- glassine PE foam synthetic rubber
- Total thickness
- Color
- Thickness of liner

1600 μm black/white 70 μm





# **Product Information**

### **Properties/Performance Values**

<ul> <li>Elongation at break</li> <li>Tensile strength</li> <li>Ageing resistance (UV)</li> <li>Chemical resistance</li> </ul>	180 % 12 N/cm medium medium	<ul> <li>Tack go</li> <li>Temperature resistance long 40 term</li> </ul>	edium ood ) °C ) °C
Adhesion to Values			
• PC (initial)	16 N/cm	• PP (initial) 16	N/cm
<ul> <li>PC (after 14 days)</li> </ul>	16 N/cm	• PP (after 14 days) 16	N/cm
• PE (initial)	16 N/cm	PVC (initial)     16	N/cm
• PE (after 14 days)	16 N/cm	• PVC (after 14 days) 16	N/cm
• PET (initial)	16 N/cm	Steel (initial)     16	N/cm
• PET (after 14 days)	16 N/cm	• Steel (after 14 days) 16	N/cm

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.