



tesa® 4174

Product Information



Fineline tape for design painting in the automotive industry

Product Features

- Excellent masking performance on painted and non-painted substrates
- No ghosting or residues until 150°C/302 °F (1h)
- Good conformability with multidimensional surfaces
- Edge does not lift off and residue-free removal

Application Fields

tesa® 4174 is suitable for various types of masking applications.

Example applications are:

- Masking of painted and non-painted substrates (e.g. automotive plastic parts) that require sharp and flat paint edges
- Two-tone car body masking

To ensure the highest performance possible, our aim is to fully understand your application (including the substrates involved) in order to provide the right product recommendation.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|----------------|-------------------|----------|
| • Backing | PVC film | • Total thickness | 110 µm |
| • Type of adhesive | natural rubber | | 4.3 mils |

Properties/Performance Values

- | | | | |
|--------------------|------------------------|----------------------------|-----------|
| • Tensile strength | 25 N/cm
14.3 lbs/in | • Hand tearability | very good |
| • Easy to remove | yes | • Suitable for die cutting | yes |

Adhesion to Values

- | | |
|---------|------------------------|
| • Steel | 3.7 N/cm
33.8 oz/in |
|---------|------------------------|

Additional Information

tesa® 4174 in small width (<10mm): adhesion to steel = 2,4N/cm 21.9 oz/in

For latest information on this product please visit <http://l.tesa.com/?ip=04174>



tesa® 4174

Product Information

Additional Information

tesa® 4174 is also available for converting and die-cutting with a paper liner 4174 PV4: adhesion to steel = 4.4N/cm, peel off force from liner = 14 cN/cm 1.3 oz/in

Also available as customized die cuts upon request as tesa® 54174

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04174>