



tesa[®] 6965 - Team 4965 Fingerlift



Product Information

205µm / 8.1 mils double sided transparent PET film tape with fingerlift

Product Description

tesa[®] 6965 - Team 4965 Fingerlift is a transparent, double-sided industrial mounting tape with fingerlift consisting of a PET backing and a modified acrylic adhesive. The double-sided mounting tape is a fingerlift version of tesa[®] 4965 Original and its adhesive is based on a patented and protected product technology. tesa[®] 6965 - Team 4965 Fingerlift is used in various different industries, frequently used for closing corrugated-board cartons or mounting different profiles. The tackified acrylic adhesive provides reliable bonding performance even at high temperatures and on rough cardboard surfaces. tesa[®] 6965 - Team 4965 Fingerlift comes with a fingerlift (extended liner) for convenient liner removal and is recycling friendly according to the INGEDE method.

Several products are equipped with this unique and high performing product design and together these products make up Team 4965. This double-sided film tape assortment helps to easily select the most efficient tape based on customer demands, products, and processes. Explore the benefits of the full tesa[®] 4965 assortment here:

<https://www.tesa.com/en-us/industry/general-applications/mounting/team-4965-assortment>

Product Features

- Fast liner removal due to fingerlift
- High initial adhesion for fast closure
- Immediate usability right after assembly
- Reliable bonding performance even at high temperatures and on rough corrugated-board surfaces
- Recycling friendly according to the INGEDE method

Application Fields

- tesa[®] 6965 - Team 4965 Fingerlift is especially designed for the closure of corrugated-board cartons
- Rubber/EPDM profile mounting
- Mounting decorative profiles and moldings in the furniture industry
- ABS plastic parts mounting in the car industry

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------------------------|
| • Backing | PET film | • Total thickness | 205 µm |
| • Type of adhesive | tackified acrylic | • Color | 8.1 mils
transparent |

For latest information on this product please visit <http://l.tesa.com/?ip=06965>



tesa[®] 6965

- Team 4965 Fingerlift

Product Information

Properties/Performance Values

• Elongation at break	50 %	• Static shear resistance at 23°C	very good
• Tensile strength	20 N/cm	• Static shear resistance at 40°C	very good
	11.4 lbs/in	• Tack	good
• Ageing resistance (UV)	good	• Temperature resistance long term	100 °C
• Chemical Resistance	good		212 °F
• Humidity resistance	very good	• Temperature resistance min.	-40 °C
• Softener resistance	good		-40 °F
		• Temperature resistance short term	200 °C
			392 °F

Adhesion to Values

• ABS (initial)	10.3 N/cm	• PET (after 14 days)	9.5 N/cm
	94.1 oz/in		86.8 oz/in
• ABS (after 14 days)	12 N/cm	• PP (initial)	6.8 N/cm
	109.6 oz/in		62.1 oz/in
• Aluminium (initial)	9.2 N/cm	• PP (after 14 days)	7.9 N/cm
	84.1 oz/in		72.2 oz/in
• Aluminium (after 14 days)	10.6 N/cm	• PS (initial)	10.6 N/cm
	96.8 oz/in		96.8 oz/in
• PC (initial)	12.6 N/cm	• PS (after 14 days)	12 N/cm
	115.1 oz/in		109.6 oz/in
• PC (after 14 days)	14 N/cm	• PVC (initial)	8.7 N/cm
	127.9 oz/in		79.5 oz/in
• PE (initial)	5.8 N/cm	• PVC (after 14 days)	13 N/cm
	53 oz/in		118.8 oz/in
• PE (after 14 days)	6.9 N/cm	• Steel (initial)	11.5 N/cm
	63 oz/in		105.1 oz/in
• PET (initial)	9.2 N/cm	• Steel (after 14 days)	11.8 N/cm
	84.1 oz/in		107.8 oz/in

Additional Information

Liner variants:

- PV0: red MOPP film (80µm / 3.2 mils; 72g/m²)
- PV2: brown glassine paper (78µm / 3.1 mils; 90g/m²)
- PV8: white MOPP friction liner (80µm / 3.2 mils; 72g/m²)

For spools, it is recommended to use tesa[®] dispensers to achieve optimal results.



tesa[®] 6965 - Team 4965 Fingerlift

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=06965>