

tesa HAF® 8405

Product Information



30µm / 1.2 mils amber reactive structural bonding film

Product Description

tesa HAF® 8405 is a reactive heat activated film based on phenolic resin and nitrile rubber. This amber double sided tape has no backing. It is protected by a strong paper liner and can easily be slit and die cut.

It is activated by heat and pressure applied over a certain period of time.

Product Features

- · Very high bonding strength
- · High temperature resistance
- · Excellent chemical resistance
- · Resistance against oil and solvents
- · Bonds remain flexible and elastic

Application Fields

It is suitable for bonding of all thermal resistant materials such as metal, glass, plastic, wood and textiles.

- High-strength splicing (overlap splice)
- Structural bonding
- · Magnet bonding in electric motors
- · Friction liners for clutches

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

•	Backing	none	•	Total thickness	30 μm
•	Type of adhesive	nitrile rubber /			1.2 mils
		phenolic resin	•	Color	amber
•	Type of liner	glassine			

Properties/Performance Values

•	Bonding strength (dynamic	12 N/mm ²	 Bonding strength (push-out) 	2 N/mm ²
	shear)			

Additional Information

Processing



tesa HAF® 8405

Product Information

Additional Information

tesa HAF® 8405 is not self adhesive. It is activated by heat and pressure over a certain interval. The following values are recommendations for machine parameters to start with. Please note that optimum parameters strongly depend on the type of machine, particular materials as well as customer requirements.

- 1. Pre-lamination: tesa HAF® 8405 is laminated before curing. For this process we recommend a temperature between $120^{\circ}\text{C} / 248^{\circ}\text{F}$ and $140^{\circ}\text{C} / 284^{\circ}\text{F}$.
- 2. Bonding: The bonding conditions temperature, pressure and time depend on the application. Following parameters can be regarded as a guideline:

Splicing application:

• Temperature: 120-220 °C (248-428 °F)

Pressure: >2 barTime: 15–90 s.

Friction liners for clutches:

• Temperature: 180-230 °C (356-446 °F)

Pressure: > 8 barTime: 3–30 min

Magnet bonding:

• Temperature: 140-180 °C (284-356 °F)

• Pressure > 6-10 bar

• Time: 2-5 min

Structural bonding:

• Temperature: 180-220 °C (356-428 °F)

Pressure: > 10-15 barTime: > 3-30 min

Bonding strength values were obtained under standard laboratory conditions. Value is guaranteed clearance limit checked with each production batch (Material: Etched aluminum test specimen / Bonding conditions: temperature = 120 °C / 248 °F; pressure = 10 bar; time = 8 min). To reach maximum bonding strength surfaces should be clean and dry.



tesa HAF® 8405

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

