



tesa® 66108

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PE foam	• Total thickness	800 µm
• Type of adhesive	tackified acrylic		31.5 mils
• Type of liner	paper	• Color	black
		• Color of liner	white with tesa logo

Product Assortment

• Available colors	black	• Available thicknesses	0.8 mm
• Available liners	PE-coated paper		

Properties/Performance Values

• Elongation at break	190 %	• Static shear resistance at 70°C	good
• Tensile strength	8 N/cm	• Tack	very good
	4.6 lbs/in	• Temperature resistance long term	80 °C
• Ageing resistance (UV)	good		176 °F
• Humidity resistance	good	• Temperature resistance short term	80 °C
• Static shear resistance at 23°C	very good		176 °F

Adhesion to Values

• ABS (initial)	10 N/cm	• PC (after 14 days)	10 N/cm
	91.4 oz/in		91.4 oz/in
• ABS (after 14 days)	10 N/cm	• PET (initial)	10 N/cm
	91.4 oz/in		91.4 oz/in
• ABS (covered side, after 14 days)	10 N/cm	• PET (after 14 days)	10 N/cm
	91.4 oz/in		91.4 oz/in
• PC (initial)	10 N/cm	• PET (covered side, after 14 days)	10 N/cm
	91.4 oz/in		91.4 oz/in



tesa® 66108

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=66108>