



**Product Information** 



## $200\mu m/7.9$ mils double sided black high performance filmic tape

#### **Product Description**

tesa® 61395 is a black, double sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 200µm/7.9 mils
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

#### **Application Fields**

- Lens mounting in mobile phones
- Touch panel mounting

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li><li>Type of liner</li><li>Total thickness</li></ul>	PET film tackified acrylic glassine 200 μm 7.9 mils	<ul> <li>Color</li> <li>Color of liner</li> <li>Thickness of liner</li> <li>Weight of liner</li> </ul>	black white with tesa logo 69 μm 2.7 mils 80 g/m <sup>2</sup>		
Properties/Performance Values					
Elongation at break	50 %	• Static shear resistance at 23°C	good		
<ul> <li>Tensile strength</li> </ul>	20 N/cm	<ul> <li>Static shear resistance at 40°C</li> </ul>	good		
	11.4 lbs/in	<ul> <li>Temperature resistance long</li> </ul>	100 °C		
<ul> <li>Ageing resistance (UV)</li> </ul>	very good	term	212 °F		
Humidity resistance	very good	Temperature resistance short	200 °C		

Temperature resistance short 200 °C 392 °F





# **Product Information**

#### **Adhesion to Values**

ABS (initial)	10 N/cm
	91.4 oz/in
<ul> <li>ABS (after 14 days)</li> </ul>	13.3 N/cm
	121.5 oz/in
• ABS (covered side, after 14	13.5 N/cm
days)	123.3 oz/in
<ul> <li>ABS (covered side, initial)</li> </ul>	10.4 N/cm
	95 oz/in
<ul> <li>Glass (initial)</li> </ul>	14.4 N/cm
	131.6 oz/in
<ul> <li>Glass (after 14 days)</li> </ul>	16.7 N/cm
	152.6 oz/in
<ul> <li>PC (initial)</li> </ul>	11.6 N/cm
	106 oz/in
<ul> <li>PC (after 14 days)</li> </ul>	19.8 N/cm
	180.9 oz/in

٠	PC (covered side, after 14 days)	19.5 N/cm 178.2 oz/in
٠	PC (covered side, initial)	11.6 N/cm
•	PMMA (initial)	106 oz/in 14.2 N/cm
•	PMMA (after 14 days)	129.7 oz/in 19.2 N/cm
	Steel (initial)	175.4 oz/in 14.3 N/cm
		130.6 oz/in
٠	Steel (after 14 days)	17 N/cm 155.3 oz/in
٠	Steel (covered side, after 14 days)	17 N/cm 155.3 oz/in
•	Steel (covered side, initial)	14.8 N/cm 135.2 oz/in

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.