



tesa[®] 61375

Product Information

tesa[®] 61375 is a 125µm black double-sided filmic tape

Product Description

tesa[®] 61375 is a black, double-sided self-adhesive tape consisting of a polyester (PET) backing and a tackified acrylic adhesive.

Special features:

- Thickness: 125µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Excellent resistance to demanding environmental conditions
- Black color

Product Features

- Thickness: 125µm
- Very high bonding strength
- Superior push out resistance
- Excellent resistance to demanding environmental conditions
- High shock resistance

Application Fields

- Lens mounting in mobile phones
- Touch panel mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

| | | | |
|--------------------|-------------------|----------------------|----------------------|
| • Backing | PET film | • Color | black |
| • Type of adhesive | tackified acrylic | • Color of liner | white with tesa logo |
| • Type of liner | glassine | • Thickness of liner | 71 µm |
| • Total thickness | 125 µm | | 2.8 mils |
| | 4.9 mils | • Weight of liner | 80 g/m ² |



tesa® 61375

Product Information

Properties/Performance Values

| | | | |
|-----------------------------------|-------------|-------------------------------------|------------------|
| • Elongation at break | 50 % | • Static shear resistance at 40°C | good |
| • Tensile strength | 20 N/cm | • Tack | medium |
| | 11.4 lbs/in | • Temperature resistance long term | 100 °C 212 °F |
| • Ageing resistance (UV) | very good | • Temperature resistance short term | 200 °C 392 °F |
| • Humidity resistance | very good | | |
| • Static shear resistance at 23°C | good | | |

Adhesion to Values

| | | | |
|-------------------------|-------------|-------------------------|-------------|
| • ABS (initial) | 8.7 N/cm | • PC (after 14 days) | 17.9 N/cm |
| | 79.5 oz/in | | 163.5 oz/in |
| • ABS (after 14 days) | 12.8 N/cm | • PMMA (initial) | 13 N/cm |
| | 116.9 oz/in | | 118.8 oz/in |
| • Glass (initial) | 12.8 N/cm | • PMMA (after 14 days) | 16.8 N/cm |
| | 116.9 oz/in | | 153.5 oz/in |
| • Glass (after 14 days) | 15.2 N/cm | • Steel (initial) | 13.9 N/cm |
| | 138.9 oz/in | | 127 oz/in |
| • PC (initial) | 11.2 N/cm | • Steel (after 14 days) | 16.7 N/cm |
| | 102.3 oz/in | | 152.6 oz/in |

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=61375>