

# tesa® 61895 SPT Series

**Product Information** 

#### $200\mu$ m/7.9 mils d/s black Shock and Push-out Technology filmic tape

### **Product Description**

tesa® 61895 is a double-sided self-adhesive tape consisting of a black PET backing equipped with a novel acrylic adhesive.

Special features:

- Very high bonding strength
- Outstanding push-out resistance
- Outstanding shock resistance
- Good LSE performance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

#### **Product Features**

- Very high bonding strength
- Outstanding push-out resistance
- Outstanding shock resistance
- Good LSE performance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

# **Application Fields**

- Cover lens mounting in electronic devices
- Touch panel mounting in electronic devices

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

# **Product Construction**

٠	Backing	PET film	•	Color	black
•	Type of adhesive	modified acrylic	٠	Color of liner	transparent
•	Type of liner	PET	•	Thickness of liner	50 µm
•	Total thickness	200 µm			2 mils
		7.9 mils	•	Weight of liner	70 g/m <sup>2</sup>



# tesa® 61895 SPT Series

# **Product Information**

### **Properties/Performance Values**

<ul> <li>Elongation at break</li> <li>Tensile strength</li> <li>Ageing resistance (UV)</li> <li>Humidity resistance</li> <li>Static shear resistance at 23°C</li> </ul>	50 % 20 N/cm 11.4 lbs/in very good very good good	<ul> <li>Static shear resistance at 40°C</li> <li>Tack</li> <li>Temperature resistance long term</li> <li>Temperature resistance short term</li> </ul>	good medium 100 °C 212 °F 200 °C 392 °F
Adhesion to Values			
• PC (initial)	14 N/cm 127.9 oz/in	• Steel (initial)	14 N/cm 127.9 oz/in
• PC (after 14 days)	17 N/cm 155.3 oz/in	• Steel (after 14 days)	15 N/cm 137 oz/in

#### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

