



tesa[®] 58326

Product Information



tesa[®] 58326

Product Description

tesa[®] 58326 is a 1200 µm/47.2 mils thermally conductive pad. This acrylic based thermally conductive product provides high thermal conductivity with its thermally conductive fillers when it is applied between heat source and heat sink to transfer the heat. Besides that, it also has excellent electrical insulation property and flame retardancy.

Product Features

- This product is equipped with special acrylic adhesive that provide certain thermal conductivity when it applies between heat source and heat sink.
- It has good performance on polar substrates.

Application Fields

Applied between heat source and heat sink to transfer the heat:

- EV battery between module and cooling system
- Power electronics between chips
- PCB and heat sink

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	none	• Color	white
• Type of adhesive	acrylic	• Color of liner	transparent
• Type of liner	PET film	• Thickness of liner	75 µm
• Total thickness	1200 µm 47.2 mils		3 mils

Product Assortment

• Available colors	white	• Available liners	PET film
• Available formats	Log roll, A4 sheet	• Available thicknesses	1200



tesa[®] 58326

Product Information

Properties/Performance Values

• Breakdown voltage	15 KV	• Temperature resistance (-40°C)	very good
• Density	1.9 g/cm ³	• Temperature resistance (125°C)	very good
• Flame retardancy	V0	• Temperature resistance short term	200 °C 392 °F
• Hardness - Shore 00	87 STK	• Thermal conductivity z-direction	2 W/mK
• Release of liner	easy	• Volume Resistance	1000000000 Ohm.cm
• Surface resistance	1000000000 Ohm.cm		

Adhesion to Values

• Aluminium (20min @ RT, 90°)	0.65 N/cm 5.9 oz/in	• Steel (20min @ RT, 90°)	0.55 N/cm 5 oz/in
• Steel (initial)	0.55 N/cm 5 oz/in		

Storage Conditions

Storage Conditions

- Temperature: from +5 to +30 Degree Celsius
- Relative humidity: from 10% to 90%
- Precautions: protect for direct sun light, do not store outside
- Other storage advices: avoid mechanical impacts and short overheating

Additional Information

The values in this section should be considered as average figures or typical only and should not be used for specification purposes.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=58326>