



Product Information



tesa® 58326

Product Description

tesa[®] 58326 is a 1200 μ m/47.2 mils thermally conductive pad. This acrylic based thermally conductive product provides high thermal conductivity with its thermally conductive fillers when it is applied between heat source and heat sink to transfer the heat. Besides that, it also has excellent electrical insulation property and flame retardancy.

Application Fields

Applied between heat source and heat sink to transfer the heat:

- EV battery between module and cooling system
- Power electronics between chips
- PCB and heat sink

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

BackingType of adhesiveType of linerTotal thickness	none • acrylic • PET film • 1200 µm 47.2 mils	Color Color of liner Thickness of liner	white transparent 75 µm 3 mils			
Product Assortment						
Available colorsAvailable formats	Log roll, A4 sheet	Available liners Available thicknesses	PET film 1200			
Properties/Performance Values						
 Breakdown voltage Density Flame retardancy Hardness - Shore 00 Release of liner 	15 KV • 1.9 g/cm ³ • V0 • 87 STK easy •	Temperature resistance (-40°C) Temperature resistance (125°C) Temperature resistance short term Thermal conductivity z-direction	very good very good 150 °C 302 °F 2 W/mK			





Product Information

Adhesion to Values

•	Aluminium	(20min	@ RT,	, 90°)	0.65 N/cm
---	-----------	--------	-------	--------	-----------

Steel (initial)
 5.9 oz/in
 0.55 N/cm
 5 oz/in

Steel (20min @ RT, 90°)

0.55 N/cm 5 oz/in

Storage Conditions

Storage Conditions

- Temperature: from +5 to +30 Degree Celsius
- Relative humidity: from 10% to 90%
- Precautions: protect for direct sun light, do not store outside
- Other storage advices: avoid mechanical impacts and short overheating

Additional Information

The values in this section should be considered as average figures or typical only and should not be used for specification purposes.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

