

tesa® 51962

Product Information



$50 \mu m / 2 mil double sided PET film tape$

Product Description

tesa® 51962 is a transparent, double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive. The double-sided tape is especially designed for the converter and tape specialist business.

Product Features

- · Excellent combination of high initial tack and immediate adhesion
- Full suitability for long-term applications
- Good handling performance in converting processes
- High resistance to demanding environmental conditions

Application Fields

tesa® 51962 is used in different industries for general mounting and laminating applications.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

| Backing | PET | • | Color | transparent |
|------------------|---|---|---|---|
| Type of adhesive | tackified acrylic | • | Color of liner | brown/blue logo |
| Type of liner | glassine | • | Thickness of liner | 69 μm |
| Total thickness | 50 μm | | | 2.7 mils |
| | 2 mils | • | Weight of liner | 80 g/m ² |
| ſ | Backing Type of adhesive Type of liner Total thickness | Type of adhesive tackified acrylic Type of liner glassine Total thickness 50 μm | Type of adhesive tackified acrylic • Type of liner glassine • Total thickness 50 μm | Fype of adhesive tackified acrylic • Color of liner Fype of liner glassine • Thickness of liner Fotal thickness 50 μm |

Properties/Performance Values

| Elongation at breakTensile strength | 50 % 20 N/cm 11.4 lbs/in | • Tack | medium good 100°C |
|--|-------------------------------------|------------------------------|----------------------------|
| Ageing resistance (UV)Humidity resistanceSoftener resistance | very good very good very good | Temperature resistance short | 212 °F 200 °C 392 °F |



tesa® 51962

Product Information

Adhesion to Values

| ABS (initial) | 5 N/cm 45.7 oz/in | • PE (after 14 days) | 2.8 N/cm 25.6 oz/in |
|---------------------------|------------------------|-------------------------------------|------------------------|
| ABS (after 14 days) | 6.1 N/cm 55.7 oz/in | PET (initial) | 5.2 N/cm 47.5 oz/in |
| Aluminium (initial) | 5 N/cm | • PET (after 14 days) | 5.8 N/cm |
| Aluminium (after 14 days) | 45.7 oz/in 6 N/cm | PP (initial) | 53 oz/in 4 N/cm |
| DC (:::::::1) | 54.8 oz/in | DD (after 44 decre) | 36.5 oz/in |
| PC (initial) | 5.3 N/cm 48.4 oz/in | PP (after 14 days) | 4 N/cm 36.5 oz/in |
| • PC (after 14 days) | 6.6 N/cm 60.3 oz/in | Steel (initial) | 5 N/cm 45.7 oz/in |
| • PE (initial) | 2 N/cm 18.3 oz/in | Steel (after 14 days) | 7.2 N/cm 65.8 oz/in |

Additional Information

Liner variants:

• PV20: branded brown glassine paper (69μm / 2.7 mil; 80g/m²)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

