




tesa® 61775

Product Information



125µm black d/s filmic high performance tape

Product Description

tesa® 61775 is a double sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 125µm
- High bonding strength
- High push out resistance
- Superior shock resistance
- Excellent resistance to demanding environmental conditions
- Black colour

Application Fields

- Lens mounting in mobile phones
- Touch panel mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Type of liner	glassine	• Color	black, beige
• Backing material	PET film	• Color of liner	white with tesa logo
• Type of adhesive	tackified acrylic, acrylic, advanced acrylic, modified acrylic	• Thickness of liner	71 µm 2.8 mils
• Total thickness	125 µm 4.9 mils		

Properties/Performance Values

• Elongation at break	50 %	• Static shear resistance at 40°C	good
• Tensile strength	20 N/cm 11.4 lbs/in	• Tack	medium, good
• Humidity resistance	very good	• Temperature resistance long term	100 °C 212 °F
• Softener resistance	good	• Temperature resistance short term	200 °C 392 °F
• Static shear resistance at 23°C	good		

For latest information on this product please visit <http://l.tesa.com/?ip=61775>



tesa® 61775

Product Information

Adhesion to Values

• ABS (initial)	9.7 N/cm 88.6 oz/in	• PC (after 14 days)	14.1 N/cm 128.8 oz/in
• ABS (after 14 days)	12.2 N/cm 111.5 oz/in	• PE (initial)	5.2 N/cm 47.5 oz/in
• Aluminium (initial)	8.8 N/cm 80.4 oz/in	• PE (after 14 days)	5.4 N/cm 49.3 oz/in
• Aluminium (after 14 days)	9.9 N/cm 90.4 oz/in	• PMMA (initial)	12.2 N/cm 111.5 oz/in
• Glass (initial)	11.6 N/cm 106 oz/in	• PMMA (after 14 days)	13.6 N/cm 124.3 oz/in
• Glass (after 14 days)	12.2 N/cm 111.5 oz/in	• Steel (initial)	11 N/cm 100.5 oz/in
• PC (initial)	12.2 N/cm 111.5 oz/in	• Steel (after 14 days)	11.8 N/cm 107.8 oz/in

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=61775>