

# tesa® 62946

## **Product Information**



Foam mounting tape with polyester film reinforcement; 11.8 mil thickness

## **Product Description**

tesa® 62946 is a black double-sided PE (polyethylene) foam tape with a PET (polyester) film reinforcement. The tape is equipped with a tackified acrylic adhesive.

#### tesa® 62946 features:

- Thickness: 300µm, 11.8 mils
- · Very high bonding strength
- · A highly conformable foam backing that compensates for design tolerances or uneven surfaces
- Excellent sealing function versus humidity and dust
- · Dampening properties offer good shock absorption
- · Easy converting and handling due to PET reinforcement
- · Very good humidity resistance
- Black color for easy detection or design purposes

#### **Application Fields**

- Touch panel / lens mounting in mobile phones
- Speaker module mounting
- · Front panel mounting in notebooks
- · Mounting on uneven surfaces

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### **Product Construction**

•	Type of liner	glassine	•	Total thickness	300 μm
•	Weight of liner	80 g/m <sup>2</sup>			11.8 mils
•	Backing material	PE foam	•	Color	black, beige
•	Type of adhesive	tackified acrylic,	•	Color of liner	brown
		acrylic, advanced	•	Thickness of liner	71 μm
		acrylic, modified			2.8 mils
		acrylic			



## tesa® 62946

## **Product Information**

Elongation at break

## Properties/Performance Values

<ul> <li>Tensile strength</li> <li>Ageing resistance (UV)</li> </ul>	23 N/cm 13.1 lbs/in very good	<ul> <li>Static shear resistance at 40°C</li> <li>Tack</li> <li>Temperature resistance long</li> </ul>	good medium, good 70 °C
<ul><li>Humidity resistance</li><li>Softener resistance</li></ul>	very good medium, good	<ul><li>term</li><li>Temperature resistance short term</li></ul>	158 °F 80 °C 176 °F
Adhesion to Values			
ABS (initial)	6.7 N/cm 61.2 oz/in	PE (initial)	2.3 N/cm 21 oz/in
ABS (after 14 days)	9.4 N/cm 85.9 oz/in	PE (after 14 days)	2.7 N/cm 24.7 oz/in
Aluminium (initial)	5.3 N/cm 48.4 oz/in	PET (initial)	5.3 N/cm 48.4 oz/in
Aluminium (after 14 days)	10.9 N/cm 99.6 oz/in	PET (after 14 days)	7.7 N/cm 70.3 oz/in
Glass (initial)	7.3 N/cm 66.7 oz/in	• PVC (initial)	6.7 N/cm 61.2 oz/in
Glass (after 14 days)	12 N/cm 109.6 oz/in	PVC (after 14 days)	13.7 N/cm 125.2 oz/in
PC (initial)	7.6 N/cm 69.4 oz/in	Steel (initial)	6.4 N/cm 58.5 oz/in
<ul> <li>PC (after 14 days)</li> </ul>	12.2 N/cm	<ul> <li>Steel (after 14 days)</li> </ul>	13.2 N/cm

Static shear resistance at 23°C good

#### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

120.6 oz/in

111.5 oz/in