




tesa® 68552

Product Information



50µm d/s filmic tape with a thin, conformable PET backing

Product Description

tesa® 68552 is a transparent, doublesided self-adhesive tape consisting of a thin, conformable PET film backing and a tackified acrylic adhesive.

tesa® 68552 features:

- Thickness: 50 µm
- High adhesion level
- Excellent conformability and adjustment to curved surfaces
- Excellent resistance to demanding environmental conditions

Application Fields

- Mounting of metal or plastic badges and signs
- Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	PET film	• Total thickness	50 µm
• Type of adhesive	tackified acrylic, acrylic, advanced acrylic, modified acrylic	• Color	2 mils transparent, optically clear

Properties/Performance Values

• Elongation at break	50 %	• Static shear resistance at 23°C	good
• Tensile strength	7 N/cm 4 lbs/in	• Static shear resistance at 40°C	medium, good
• Ageing resistance (UV)	very good	• Tack	medium, good
• Chemical resistance	very good	• Temperature resistance long term	100 °C 212 °F
• Humidity resistance	very good	• Temperature resistance short term	200 °C 392 °F



tesa[®] 68552

Product Information

Adhesion to Values

• ABS (initial)	6.1 N/cm 55.7 oz/in	• PET (after 14 days)	6.5 N/cm 59.4 oz/in
• ABS (after 14 days)	7.3 N/cm 66.7 oz/in	• PP (initial)	3 N/cm 27.4 oz/in
• Aluminium (initial)	5.7 N/cm 52.1 oz/in	• PP (after 14 days)	4.5 N/cm 41.1 oz/in
• Aluminium (after 14 days)	7.4 N/cm 67.6 oz/in	• PS (initial)	6 N/cm 54.8 oz/in
• PC (initial)	7.4 N/cm 67.6 oz/in	• PS (after 14 days)	7.7 N/cm 70.3 oz/in
• PC (after 14 days)	8.9 N/cm 81.3 oz/in	• PVC (initial)	6.3 N/cm 57.6 oz/in
• PE (initial)	3.2 N/cm 29.2 oz/in	• PVC (after 14 days)	10 N/cm 91.4 oz/in
• PE (after 14 days)	4.2 N/cm 38.4 oz/in	• Steel (initial)	7 N/cm 64 oz/in
• PET (initial)	6.1 N/cm 55.7 oz/in	• Steel (after 14 days)	8.6 N/cm 78.6 oz/in

Additional Information

Liner variants:

PV40 white/red logo glassine paper (71µm; 82g/m²)

PV50 transparent PET liner (50µm; 72g/m²)

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=68552>