




tesa[®] 70435

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	none	• Color	white
• Type of adhesive	specialty	• Color of liner	brown
• Type of liner	glassine	• Thickness of liner	72 µm
• Total thickness	350 µm 13.8 mils		2.8 mils

Properties/Performance Values

• Removability after 14 days (23°C)	very good	• Static shear resistance at 40°C	very good
• Residue free removal	yes	• Temperature resistance long term	60 °C 140 °F
• Solvent free	yes	• Temperature resistance short term	90 °C 194 °F
• Static shear resistance at 23°C	very good		

Adhesion to Values

• Aluminium (initial)	13 N/cm 118.8 oz/in	• PE (initial)	10 N/cm 91.4 oz/in
• Aluminium (after 14 days)	13 N/cm 118.8 oz/in	• PE (after 14 days)	10 N/cm 91.4 oz/in
• Magnesium (initial)	12 N/cm 109.6 oz/in	• Steel (initial)	20 N/cm 182.7 oz/in
• Magnesium (after 14 days)	12 N/cm 109.6 oz/in	• Steel (after 14 days)	20 N/cm 182.7 oz/in



tesa[®] 70435

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=70435>