# tesa® 62622



## **Product Information**

#### 150µm double-sided black high performance foam tape

tesa® 62622 is a black double-sided thin foam tape. The tape is equipped with a tackified acrylic adhesive.

tesa® 62622 features:

- Thickness: 150µm
- Very high bonding strength
- Highly conformable foam backing provides excellent shock resistance
- Superior push out resistance due to strong high performance adhesive
- Good sealing function versus humidity and dust
- Waterproofness

#### Main Application

- Touch panel mounting
- Lens mounting in mobile phones
- LCD cover / front panel mounting in notebooks
- Mounting on uneven and rough surfaces

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Technical Data**

<ul><li>Color</li><li>Total thickness</li></ul>	PE foam black 150 μm 5.9 mils tackified acrylic	<ul><li>Elongation at break</li><li>Tensile strength</li><li>Type of liner</li><li>Thickness of liner</li></ul>	380 % 12 N/cm 6.9 lbs/in PET 50 μm 2 mils
Adhesion to			
• Steel (initial)	13.0 N/cm 118.8 oz/in	• Steel (after 14 days)	13.0 N/cm 118.8 oz/in
ABS (initial)	10.0 N/cm 91.4 oz/in	• ABS (after 14 days)	14.0 N/cm 127.9 oz/in
Aluminium (initial)	12.0 N/cm 109.6 oz/in	Aluminium (after 14 days)	13.0 N/cm 118.8 oz/in
• Glass (initial)	13.5 N/cm 123.3 oz/in	• Glass (after 14 days)	13.5 N/cm 123.3 oz/in
• PC (initial)	13.0 N/cm 118.8 oz/in	• PC (after 14 days)	13.0 N/cm 118.8 oz/in
• PMMA (initial)	13.0 N/cm 118.8 oz/in	• PMMA (after 14 days)	13.0 N/cm 118.8 oz/in
Properties			
Temperature resistance short term	90 °C 194 °F	Temperature resistance long term	80 °C 176 °F





#### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

