



tesa® 54332

Heat Performance Sealer



Product Information

The Heat Performance Sealer for permanent hole covering applications

Product Description

tesa® 54332 combines an extremely heat-resistant aluminum laminated glasscloth layer with an extra thick acrylic adhesive sealer. This product is optimized for the automotive industry to cover unused interior holes that require excellent heat resistance and perfect sealing.

Main features:

- Extreme temperature resistance up to 200°C/392°F for 30 minutes
- Reliable corrosion protection, e.g. punch burrs will be securely sealed by 800µm/31.5 mil adhesive layer
- Noise reduction regardless of the hole dimension
- Secure adhesion to painted substrates and reinforced plastic substrates in automotive lightweight constructions, e.g. CFRP

Application Fields

tesa® 54332 Heat Performance Sealer is especially suitable for permanent hole covering applications that are directly exposed to heat radiation.

To ensure the highest performance possible, our aim is to fully understand your application (including the substrates involved) in order to provide the right product recommendation.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------------------|--------------------|------------------|
| • Type of liner | PE-coated paper | • Type of adhesive | modified acrylic |
| • Backing material | aluminum laminated glasscloth | • Color | silver |

Properties/Performance Values

- | | |
|-----------------------|-------|
| • Puncture resistance | 400 N |
|-----------------------|-------|

Adhesion to Values

- | | |
|---------|-----------|
| • Steel | 22 N/cm |
| | 201 oz/in |



tesa® 54332

Heat Performance Sealer

Product Information

Additional Information

tesa® 54332 can be supplied in customer specific dimensions according to customer requirements and applications in either roll or sheet form.

tesa's automation and application solution department provides customised equipment and self-designed application tools to enhance productivity.

Adhesion value refers to the acrylic adhesive layer which has been reinforced by a 36µm/1.4 mil d/s etched PET, measured on ASTM-Steel after 3 days of dwell time at RT.

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=54332>