



# tesa® 64958

## Product Information



### Double-sided PE foam tape

### Product Description

tesa® 64958 is a white double-sided tape with a PE-foam backing and a synthetic rubber adhesive.

tesa® 64958 features:

- Highly conformable PE-foam
- High immediate bonding strength even on rough or uneven surfaces
- High bonding strength at low mounting pressure
- High bonding strength on low surface energy substrates

### Application Fields

- Construction of POS-displays
- Mounting of indoor signs and posters
- Mounting of shelf edge labelling systems
- Additional dampening and anti-rattle

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Backing material	PE foam	• Colour	white
• Type of adhesive	synthetic rubber	• Thickness of liner	70 µm
• Type of liner	glassine	• Weight of liner	80 g/m <sup>2</sup>
• Total thickness	1050 µm		

### Properties/Performance Values

• Elongation at break	200 %	• Static shear resistance at 40°C	medium
• Tensile strength	7 N/cm	• Tack	good
• Ageing resistance (UV)	medium	• Temperature resistance long term duration	40 °C
• Chemical resistance	medium	• Temperature resistance short term duration	60 °C



# tesa® 64958

## Product Information

### Adhesion to Values

• PC (initial)	4 N/cm	• PP (initial)	4 N/cm
• PC (after 14 days)	4 N/cm	• PP (after 14 days)	4 N/cm
• PE (initial)	4 N/cm	• PVC (initial)	4 N/cm
• PE (after 14 days)	4 N/cm	• PVC (after 14 days)	4 N/cm
• PET (initial)	4 N/cm	• Steel (initial)	4 N/cm
• PET (after 14 days)	4 N/cm	• Steel (after 14 days)	4 N/cm

### Additional Information

Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC, PE
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC, PP, PE

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=64958>