


tesa® ACXplus 77805

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	foamed acrylic	• Total thickness	500 µm
• Type of adhesive	LSE	• Colour	gray
• Type of liner	PE		

Properties/Performance Values

• Ageing resistance (UV)	good	• Temperature range	-40 to +80 °C
• Humidity resistance	very good	• Temperature resistance long term duration	80 °C
• Static shear resistance at 90°C	very good	• Temperature resistance short term duration	120 °C

Adhesion to Values

• ABS (initial)	24 N/cm	• Steel (initial)	26 N/cm
• ABS (after 3 days)	26 N/cm	• Steel (after 14 days)	28 N/cm
• PP (initial)	26 N/cm	• Steel (after 3 days)	28 N/cm
• PP (after 3 days)	27 N/cm		

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=77805>