

tesa® ACXplus 74712

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	foamed acrylic	• Colour	deep black
• Type of adhesive	acrylic	• Colour of liner	blue
• Type of liner	PE/PP protection film	• Type of adhesive to seal	heat-activatable
• Total thickness	1200 µm		

Product Assortment

• Available colors	deep black
--------------------	------------

Properties/Performance Values

• Elongation at break	500 %	• Ageing resistance (UV)	very good
• Tensile strength	19 N/cm	• Humidity resistance	very good

Adhesion to Values

• Clear coat (after 20 min)	18 N/cm	• Steel (after 3 days)	36 N/cm
• Clear coat (covered side, after 3 days)	36 N/cm	• TPE (T-Peel, after 3 days warm / humid)	16 N/cm
• Steel (initial)	36 N/cm	• TPE (T-Peel, after 3 days)	16 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=74712>