

tesa®

## Product Information

56491

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                    |              |                   |        |
|--------------------|--------------|-------------------|--------|
| • Backing material | Caotchouc    | • Total thickness | 660 µm |
| • Type of adhesive | butyl rubber |                   |        |

### Properties/Performance Values

- |                             |                    |                          |                                    |
|-----------------------------|--------------------|--------------------------|------------------------------------|
| • Tensile strength          | 33 N/cm            | • Residue free removal   | no                                 |
| • Abrasion resistance       | yes                | • Solvent free           | no                                 |
| • Adhesive strength         | Very high adhesion | • Suitable surfaces      | Most plastics, Steel, Glass, Metal |
| • Ageing resistance (UV)    | yes                | • Tear resistance        | yes                                |
| • Area of use               | In- and Outdoor    | • Temperature resistance | yes                                |
| • Hand tearability          | no                 | • UV-resistant           | yes                                |
| • Oil and grease resistance | yes                | • Waterproof             | yes                                |
| • Ozone resistance          | yes                | • Writable               | no                                 |

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?cp=4641DIY>