



tesa® 6720

New Bond

Product Information

200µm double-sided acrylic foam tape



Product Description

tesa® 6720 is acrylic foam tape in gray color, the AC foam works both as backing and adhesive.

Product Features

- Good bonding on various substrates
- Good temperature resistance and aging performance
- Cost-effective as entry level standard product

Application Fields

Example mounting applications include but are not limited to:

- Decoration glass and panel mounting
- Part and logo mounting
- Control panel mounting
- Stiffener mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-----------------|-------------------|--------|
| • Backing | Acrylic foam | • Total thickness | 200 µm |
| • Type of adhesive | pure acrylic | • Color | gray |
| • Type of liner | PE-coated paper | | |

Properties/Performance Values

- | | | | |
|------------------------------------|-----------|-------------------------------------|--------|
| • Static shear resistance at 23°C | very good | • Temperature resistance short term | 200 °C |
| • Temperature resistance long term | 100 °C | | |

Adhesion to Values

- | | | | |
|----------------------------|---------|------------------------|---------|
| • ABS (initial) | 6 N/cm | • Glass (after 3 days) | 16 N/cm |
| • ABS (after 3 days) | 10 N/cm | • PC (initial) | 10 N/cm |
| • Aluminium (initial) | 10 N/cm | • PC (after 3 days) | 13 N/cm |
| • Aluminium (after 3 days) | 16 N/cm | • Steel (initial) | 12 N/cm |
| • Glass (initial) | 12 N/cm | • Steel (after 3 days) | 18 N/cm |



tesa® 6720

New Bond

Product Information

Additional Information

PV01 White paper with blue logo, d/s release coating (150µm thickness)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=06720>