



**Product Information** 



## 175µm double sided black high performance filmic tape

#### **Product Description**

tesa® 61355 is a black, double sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

#### **Product Features**

- Thickness: 175µm
- Very high bonding strength
- · Superior push out resistance
- High shock resistance
- · Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

## **Application Fields**

- · Lens mounting in mobile phones
- Touch panel mounting

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

# **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li><li>Type of liner</li><li>Total thickness</li></ul>	PET film tackified acrylic glassine 175 μm	<ul><li>Color</li><li>Color of liner</li><li>Thickness of liner</li><li>Weight of liner</li></ul>	black white with tesa logo 71 μm 80 g/m²		
Properties/Performance Values					
<ul> <li>Elongation at break</li> </ul>	50 %	• Static shear resistance at 40°C	good		

term

•	Tensile strength	20 N/cm
•	Ageing resistance (UV)	very good
•	Humidity resistance	very good

•	Weight of liner	80 g/m <sup>2</sup>
•	Static shear resistance at 40°C Tack Temperature resistance long term	good medium 100 °C
•	Temperature resistance short	200 °C





# **Product Information**

### Adhesion to Values

•	ABS (initial)	9.6 N/cm
•	Glass (initial)	14.4 N/cm
•	Glass (after 14 days)	16.6 N/cm
•	PC (initial)	11.4 N/cm
•	PC (after 14 days)	19.2 N/cm

• PC (after 14 days)

PMMA (initial)	13.9 N/cm
<ul> <li>PMMA (after 14 days)</li> </ul>	19.2 N/cm
Steel (initial)	14.1 N/cm
<ul> <li>Steel (after 14 days)</li> </ul>	16.9 N/cm

# Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

