




tesa[®] 70210

Bond & Detach



Product Information

100µm d/s Superior Shock Bond & Detach with stretchable Backing

Product Description

tesa[®] 70210 is a stretch release tape equipped with a high shock adhesive

Product Features

- Thickness: 100µm
- Outstanding shock resistance
- High tear resistance
- Very high bonding strength
- Excellent push out resistance
- Easy removability by stretching the adhesive, even after a long bonding time
- Residue free removability
- IPX8

Application Fields

- Battery mounting
- Permanent mounting of components in electronic devices with the option to remove the parts for repairing or recycling
- Temporary fixation of components

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-----------|-------------------|-------------|
| • Backing | PU film | • Total thickness | 100 µm |
| • Type of adhesive | specialty | • Color | white |
| • Type of liner | PET | • Color of liner | transparent |

Properties/Performance Values

- | | | | |
|------------------------------------|-----------|-------------------------------------|-------|
| • Static shear resistance at 40°C | very good | • Temperature resistance short term | 90 °C |
| • Temperature resistance long term | 60 °C | | |

Adhesion to Values

- | | | | |
|-----------------------------|--------|-------------------------|--------|
| • Aluminium (initial) | 7 N/cm | • PE (initial) | 5 N/cm |
| • Aluminium (after 14 days) | 7 N/cm | • PE (after 14 days) | 5 N/cm |
| • Magnesium (initial) | 6 N/cm | • Steel (initial) | 7 N/cm |
| • Magnesium (after 14 days) | 6 N/cm | • Steel (after 14 days) | 7 N/cm |

For latest information on this product please visit <http://l.tesa.com/?ip=70210>



tesa[®] 70210 Bond & Detach

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=70210>