




# tesa<sup>®</sup> 67208

## tesa<sup>®</sup> Bond&Detach



### Product Information

80µm d/s High Shock Bond & Detach

### Product Description

tesa<sup>®</sup> 67208 is a double-sided mounting tape which can be removed

### Product Features

- Thickness: 80µm
- Outstanding shock resistance
- High tear resistance
- Very high bonding strength
- Excellent push out resistance
- Easy removability by stretching the adhesive
- The tape can be removed even after a long bonding time
- Residue free removability
- IPX8

### Application Fields

- Battery mounting
- Permanent mounting of components in electronic devices with the option to remove the parts for repairing or recycling
- Temporary fixation of components

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                    |           |                   |             |
|--------------------|-----------|-------------------|-------------|
| • Backing          | PU film   | • Total thickness | 80 µm       |
| • Type of adhesive | specialty | • Color           | white       |
| • Type of liner    | PET       | • Color of liner  | transparent |

### Properties/Performance Values

- |                                    |           |                                     |       |
|------------------------------------|-----------|-------------------------------------|-------|
| • Static shear resistance at 40°C  | very good | • Temperature resistance short term | 90 °C |
| • Temperature resistance long term | 60 °C     |                                     |       |



# tesa<sup>®</sup> 67208

## tesa<sup>®</sup> Bond&Detach

### Product Information

#### Adhesion to Values

• Aluminium (initial)	4 N/cm	• PE (initial)	4 N/cm
• Aluminium (after 14 days)	4 N/cm	• PE (after 14 days)	4 N/cm
• Magnesium (initial)	5 N/cm	• Steel (initial)	5 N/cm
• Magnesium (after 14 days)	5 N/cm	• Steel (after 14 days)	5 N/cm

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=67208>