

tesa® 64956

Product Information



800µm double sided PE foam tape

Product Description

tesa® 64956 is a double sided PE foam tape. The tape is equipped with a synthetic rubber adhesive.

Product Features

- Thickness: 800µm
- Excellent immediate bonding strength
- · High bonding strength even on low surface energy substrates
- Highly conformable foam backing provides high bonding strength on rough or uneven surfaces
- Multi-purpose tape suitable for hand or automatic application

Application Fields

- Bonding of trims and profiles (plastic extrusions)
- Mounting of shelf edge labelling systems
- Fixing of cable channels
- · Construction of POS-displays
- · Mounting of indoor signs
- · Assembly aid, pre-fixation

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

•	Backing	PE foam	•	Total thickness	800 μm
•	Type of adhesive	synthetic rubber	•	Color	black/white
•	Type of liner	glassine	•	Thickness of liner	70 μm

Properties/Performance Values

•	Elongation at break	180 %	•	Static shear resistance at 40°C	medium
•	Tensile strength	8 N/cm	•	Tack	good
•	Ageing resistance (UV)	medium	•	Temperature resistance long	40 °C
•	Chemical Resistance	medium		term	
			•	Temperature resistance short	60 °C
				term	



tesa® 64956

Product Information

Adhesion to Values

•	ABS (initial)	12 N/cm	•	PET (after 14 days)	15 N/cm
•	ABS (after 14 days)	14 N/cm	•	PP (initial)	15 N/cm
•	PC (initial)	15 N/cm	•	PP (after 14 days)	15 N/cm
•	PC (after 14 days)	15 N/cm	•	PVC (initial)	15 N/cm
•	PE (initial)	12 N/cm	•	PVC (after 14 days)	15 N/cm
•	PE (after 14 days)	12 N/cm	•	Steel (initial)	15 N/cm
•	PET (initial)	15 N/cm	•	Steel (after 14 days)	15 N/cm

Additional Information

Liner variants:

• PV06 red MOPP film (80µm)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

