

# tesa® ACXplus 7273

## Multi Purpose (MP)



### Product Information

800 µm double-sided acrylic foam tape

### Product Description

tesa® ACX<sup>plus</sup> 7273 MP is a gray double-sided, visco-elastic acrylic foam tape.

### Product Features

- It absorbs and dissipates dynamic and static loads.
- Due to this unique formulation, it is able to compensate for thermal elongations of bonded parts.
- PFAS/PFOS free product

### Application Fields

- The tesa® ACX<sup>plus</sup> MP product family is suitable for a wide range of multi-purpose bonding applications.
- To ensure the highest performance possible, our aim is to fully understand the application (including the substrates involved) in order to provide the right product recommendation.
- tesa® ACX<sup>plus</sup> 726x MP series is especially suitable for bonding applications such as emblem, decorative part or signage mounting.

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                    |                |                   |        |
|--------------------|----------------|-------------------|--------|
| • Backing          | foamed acrylic | • Total thickness | 800 µm |
| • Type of adhesive | pure acrylic   | • Color           | gray   |

### Properties/Performance Values

- |                                    |        |                                     |        |
|------------------------------------|--------|-------------------------------------|--------|
| • Temperature resistance long term | 100 °C | • Temperature resistance short term | 200 °C |
|------------------------------------|--------|-------------------------------------|--------|

### Adhesion to Values

- |                            |         |                         |         |
|----------------------------|---------|-------------------------|---------|
| • ABS (initial)            | 1 N/cm  | • PP (after 14 days)    | 1 N/cm  |
| • ABS (after 14 days)      | 2 N/cm  | • Steel (initial)       | 16 N/cm |
| • Aluminium (after 3 days) | 35 N/cm | • Steel (after 14 days) | 28 N/cm |
| • PP (initial)             | 1 N/cm  | • Steel (after 3 days)  | 28 N/cm |

### Additional Information

Please note that we recommend using tesa® Adhesion Promoter as a surface pre-treatment. It leads to a significant improvement in adhesion levels, avoids moisture infiltration, and promotes long-term resistance against harsh

For latest information on this product please visit <http://l.tesa.com/?ip=7273>

# tesa® ACXplus 7273

## Multi Purpose (MP)

### Product Information

### Additional Information

environmental factors. Which tesa® Adhesion Promoter should be used depends on the substrates and the application. We will be glad to advise you in order to find the right solution.

Liner versions:

- PV44: White filmic liner - branded

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=7273>