



Product Information



56 μ m PCR-PET tape for Electrical Insulation applications

Product Description

tesa[®] 61001 is a 56 μm transparent PCR-PET tape with a water-based acrylic adhesive. tesa[®] 61001 was designed for electrical insulation applications.

Sustainable Aspects

- 70% Post-Consumer Recycled (PCR) PET-backing
- Water-based adhesive



For more information: https://www.tesa.com/product-sustainability

Product Features

- Dielectric breakdown and leakage current protection
- Anti-Repulsion performance
- Reworkability

Application Fields

- Cell-Wrapping
- Metal-Part Insulation

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

 Backing Post-consumer recycled content of backing Type of adhesive Type of liner 	PET 70 % water-based acrylic PET	 Total thickness Color of liner Thickness of liner Residual water content 	56 μm white 23 μm 0.05 g/m²				
Properties/Performance Values							
Electron the state state	00.0/		400.14				

•	Elongation at break	80 %	٠	CTI (backing side)	400 V
•	Tensile strength	50 N/cm	•	Electrolyte resistance	yes
•	Breakdown voltage	6 KV	•	Liner removal force	40 cN/cm
•	CTI (adhesive side)	600 V			





Product Information

Adhesion to Values

• Steel

3.5 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 26/04/24 – en-US