

tesa[®] 58377

Product Information

50 µm single-sided white flame retardant PET tape

Product Description

The 25 µm white FR PET filmic backing offers excellent electrical insulation property. The PET liner ensures it can be easily released without adhesive residue. It is equipped with FR modified acrylic to ensure the tape meet UL 94 VTM-0 FR level.

Product Features

- Very good adhesion strength on polar substrate
- Flame retardancy (UL94 VTM0 equivalent)
- Excellent electrical insulation property
- Friendly to converting process
- Halogen-free

Application Fields

- Electrical insulation protection on metal parts with FR performance
- Encapsulation of fire protection or thermal insulation material

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|------------|----------------------|-------------|
| • Backing | PET | • Total thickness | 50 µm |
| • Type of adhesive | FR acrylic | • Color of liner | transparent |
| • Type of liner | PET film | • Thickness of liner | 25 µm |

Properties/Performance Values

- | | | | |
|-----------------------|-----------|------------------------------------|--------|
| • Elongation at break | 131.9 % | • Dielectric breakdown voltage | 6000 V |
| • Tensile strength | 32.2 N/cm | • Temperature resistance long term | 85 °C |

Adhesion to Values

- | | | | |
|-----------------------------|----------|------------------------|----------|
| • Aluminium (initial) | 5.6 N/cm | • ASTM (initial) | 6.7 N/cm |
| • Aluminium (after 14 days) | 6.5 N/cm | • ASTM (after 14 days) | 7.3 N/cm |

tesa[®] 58377

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=58377>