



tesa® 54334 PV1 NoiseGuard

Product Information

Acoustic sealing patch for hole covering applications



Product Description

tesa® 54334 NoiseGuard significantly reduces and absorbs noise regardless of the hole size to enhance the acoustic comfort while driving. It is a multilayer composite, combining a outer black PET layer for superb black appearance with a thick, highly filled acrylic adhesive (1.1 kg/m^2) and a strong inner PET layer for very good noise reduction. The high-performing tackified acrylic adhesive offers excellent hold on various surfaces, including perfect sealing properties.

Product Features

- Very good acoustic insulation properties for higher drive comfort, comparable to a closed car body
- Reliable corrosion protection and sealing against water ingress
- Very good puncture resistance
- Good UBC (PVC) compatibility and reliable paint anchorage
- Stone chipping protection
- Secure adhesion to steel, aluminum, plastics, painted substrates, and reinforced plastic substrates in automotive lightweight constructions

Application Fields

- unexposed exterior holes e.g. in portected underbody or wheel arch areas
- interior holes e.g. A-pillars, doors, floor
- application before and after paint shop along the automotive production process
- seamlessly integrates with tesa's fully automated hole covering equipment ensuring ergonomic and consistent application

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	Post consumer recycled PET	• Total thickness	570 μm
• Post-consumer recycled content of backing	90 %	• Color	black
• Type of adhesive	modified acrylic	• Color of liner	brown
• Type of liner	paper	• Weight of liner	80 g/m^2



tesa[®] 54334 PV1 NoiseGuard

Product Information

Properties/Performance Values

• Area weight	1100 g/m ²	• Puncture resistance on e-coat, backing side (24 h; RT)	1000 N
• Chemical Resistance	very good	• Puncture resistance on e-coat, backing side (30 min; 160 °C)	1200 N
• Conformability	low	• Sealing performance (IPX7 acc. ISO 20653:2023-08)	yes
• Humidity sealing	very good	• Stone chip resistance (SAE J400:2012-10 Method C)	8A
• Noise damping	very good	• Temperature resistance (30 min)	160 °C
• Puncture resistance on e-coat, adhesive side (24 h; RT)	300 N	• UBC / Paint compatibility	good
• Puncture resistance on e-coat, adhesive side (30 min; 160 °C)	330 N		

Adhesion to Values

• Steel (initial)	14 N/cm
-------------------	---------

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.