

tesa® 88648

Product Information



160µm removable double coated tissue tape

Product Description

tesa® 88648 is a 160µm double coated tissue tape consisting of a strong non-woven backing and a special removable adhesive.

Product Features

High bonding strength and shear resistance

Excellent permanent removability on various substrates

Very good handling performance in converting processes

Excellent resistance to demanding environmental conditions

Application Fields

Applications requiring recycling or re-peeling

Bonding of metal, plastic and foam substrates

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

| • | Backing | non-woven | • | Total thickness | 160 μm |
|---|------------------|-------------------|---|-----------------|-----------------|
| • | Type of adhesive | tackified acrylic | • | Color | translucent |
| • | Type of liner | PE-coated paper | • | Color of liner | white/blue logo |

Properties/Performance Values

| • | Elongation at break | 25 % | • | Static shear resistance at 23°C | very good |
|---|-----------------------------------|---------|---|---------------------------------|-----------|
| • | Tensile strength | 20 N/cm | • | Tack | medium |
| • | Removability after 14 days (23°C) | good | • | Temperature resistance long | 80 °C |
| • | Residue-free removability | yes | | term | |
| | | | • | Temperature resistance short | 160 °C |
| | | | | term | |



tesa® 88648

Product Information

Adhesion to Values

| • | ABS (initial) | 8.6 N/cm | • | PMMA (initial) | 9.9 N/cm |
|---|--------------------------|-----------|---|-----------------------|-----------|
| • | ABS (after 3 days) | 11 N/cm | • | PMMA (after 3 days) | 11.3 N/cm |
| • | Aluminium (initial) | 9.2 N/cm | • | PP (initial) | 5 N/cm |
| • | Aluminium (after 3 days) | 11.3 N/cm | • | PP (after 3 days) | 6.7 N/cm |
| • | Glass (initial) | 9.2 N/cm | • | PS (initial) | 10 N/cm |
| • | Glass (after 3 days) | 9.8 N/cm | • | PVC (initial) | 7.8 N/cm |
| • | PC (initial) | 8.5 N/cm | • | Steel (initial) | 8.7 N/cm |
| • | PC (after 3 days) | 9.2 N/cm | • | Steel (after 14 days) | 13 N/cm |
| • | PET (initial) | 8.4 N/cm | • | Steel (after 3 days) | 10.2 N/cm |

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

