




tesa® 7714

Optically Clear Adhesive



Product Information

100µm pressure sensitive optically clear tape for reliable bonding

Product Features

- Pressure sensitive design
- High transmission and low haze
- Reliable bonding on different substrates
- Superior durability for temperature, humidity and UV testing

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|----------|------------------------------------|-------------|
| • Backing | none | • Color | transparent |
| • Type of adhesive | acrylic | • Color of liner | transparent |
| • Type of liner | PET film | • Thickness of easy release liner | 75 µm |
| • Total thickness | 100 µm | • Thickness of tight release liner | 75 µm |

Product Assortment

- | | |
|--------------------|-------------|
| • Available colors | transparent |
|--------------------|-------------|

Properties/Performance Values

- | | | | |
|--------------------------|-----------|------------------------------------|--------|
| • Ageing resistance (UV) | very good | • Refractive index | 1.48 |
| • Dielectric constant | 5.76 | • Temperature resistance long term | 105 °C |
| • Haze | 0.1 % | • Transmittance (380 - 780nm) > | 99 % |
| • Humidity resistance | very good | | |

Adhesion to Values

- | | | | |
|-------------------|----------|----------------|----------|
| • Glass (initial) | 8.9 N/cm | • PC (initial) | 9.5 N/cm |
|-------------------|----------|----------------|----------|

Storage Conditions

Storage Conditions

- Storage of rolls in a horizontal position at temperature +5°C to +35°C and relative humidity 20% to 60%
- Original packaging excluding exposure of tapes to light and heating source
- Avoid mechanical impacts and short overheating
- After opening the packaging, the tape shall be used as soon as possible



tesa® 7714

Optically Clear Adhesive

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=07714>