

# tesa® 69906 Optically Clear Adhesive



## **Product Information**

150  $\mu$ m UV-curable optically clear tape for curved design

#### **Product Description**

tesa® 69906 is a highly transparent transfer tape produced under controlled clean room conditions and designed for optically clear lamination for rigid or flexible substrates with curved designs. It is post UV curable tape which could be cured under UVA and UVV (<410nm) wavelength.

#### **Product Features**

- High transmittance and low haze
- Excellent temperature, humidity and UV-resistance
- Low UV curing dosage
- Excellent edge bubble suppression

#### **Application Fields**

- Optically clear lamination of curved cover designs
- Optically clear lamination of plastic cover

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li><li>Type of liner</li><li>Color</li></ul>	none acrylic PET film transparent	<ul> <li>Color of liner</li> <li>Thickness of easy release liner</li> <li>Thickness of tape</li> <li>Thickness of tight release liner</li> </ul>	transparent 50 μm 150 μm 75 μm
Properties/Performance Values			
<ul><li>Ageing resistance (UV)</li><li>Haze</li><li>Humidity resistance</li></ul>	very good 0.2 % very good	<ul> <li>Refractive index</li> <li>Tack</li> <li>Transmittance (380 - 780nm) &gt;</li> </ul>	1.48 Iow 99 %
Adhesion to Values			
<ul><li>Glass (initial)</li><li>Glass (after UV curing)</li><li>PC (initial)</li></ul>	14.2 N/cm 14.4 N/cm 13.1 N/cm	<ul><li>PC (after UV curing)</li><li>PET (initial)</li><li>PET (after UV curing)</li></ul>	14.9 N/cm 10.2 N/cm 11.7 N/cm

#### **Additional Information**

UV curing dosage suggestion

For latest information on this product please visit http://l.tesa.com/?ip=69906



# tesa® 69906 Optically Clear Adhesive

**Product Information** 

### **Additional Information**

• Above 1000mj per sq.cm (UVA 365nm) dosage on adhesive surface

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 27/03/25 – en-US