


# tesa® 60929

## Product Information



140µm double sided black non-woven tape

## Product Description

tesa® 60929 is a 140µm double sided black non-woven tape consisting of a non-woven backing and a tackified acrylic adhesive.

## Product Features

- High initial adhesion
- High peel adhesion level on various kinds of metal, plastic, paper and film surfaces
- Excellent light blocking properties
- High conformability for uneven surfaces
- Good converting properties

## Application Fields

- Permanent paper and film mounting where high peel adhesion level is needed
- Mounting and assembly of components into electronic devices

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- |                    |                   |                   |                |
|--------------------|-------------------|-------------------|----------------|
| • Backing          | non-woven         | • Total thickness | 140 µm         |
| • Type of adhesive | tackified acrylic | • Color           | black          |
| • Type of liner    | PE-coated paper   | • Color of liner  | white/red logo |

## Properties/Performance Values

- |                                   |           |                                     |        |
|-----------------------------------|-----------|-------------------------------------|--------|
| • Static shear resistance at 23°C | very good | • Temperature resistance long term  | 60 °C  |
| • Tack                            | very good | • Temperature resistance short term | 120 °C |

## Adhesion to Values

- |                     |           |                        |           |
|---------------------|-----------|------------------------|-----------|
| • PC (initial)      | 12.4 N/cm | • PI (after 3 days)    | 10.7 N/cm |
| • PC (after 3 days) | 13.5 N/cm | • Steel (initial)      | 10 N/cm   |
| • PI (initial)      | 10.2 N/cm | • Steel (after 3 days) | 11.1 N/cm |

# tesa® 60929

## Product Information

### Additional Information

The adhesion data is tested according to ASTM D3330

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=60929PV43>