


tesa® 4967

Product Information



160µm double sided transparent filmic tape

Product Description

tesa® 4967 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

Product Features

- Extremely high holding power even at elevated temperatures
- Superior converting performance due to strong PET backing and reduced adhesive mass flow
- Good bonding performance even to LSE materials

Application Fields

- Mounting lenses to mobile phone housings
- Mounting of ABS plastic parts in the automotive industry
- Mounting of decorative profiles and mouldings in the furniture industry

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------------|
| • Backing | PET film | • Total thickness | 160 µm |
| • Type of adhesive | tackified acrylic | • Color | transparent |

Properties/Performance Values

- | | | | |
|--------------------------|-----------|-------------------------------------|--------|
| • Elongation at break | 50 % | • Static shear resistance at 23°C | good |
| • Tensile strength | 20 N/cm | • Static shear resistance at 40°C | good |
| • Ageing resistance (UV) | very good | • Tack | good |
| • Chemical Resistance | good | • Temperature resistance long term | 100 °C |
| • Humidity resistance | very good | • Temperature resistance short term | 200 °C |
| • Softener resistance | good | | |

tesa® 4967

Product Information

Adhesion to Values

• ABS (initial)	9.8 N/cm	• PET (after 14 days)	10.5 N/cm
• ABS (after 14 days)	10.8 N/cm	• PP (initial)	5.3 N/cm
• Aluminium (initial)	9.6 N/cm	• PP (after 14 days)	7 N/cm
• Aluminium (after 14 days)	12.2 N/cm	• PS (initial)	10.2 N/cm
• PC (initial)	11.7 N/cm	• PS (after 14 days)	11.1 N/cm
• PC (after 14 days)	13.1 N/cm	• PVC (initial)	8.9 N/cm
• PE (initial)	5.2 N/cm	• PVC (after 14 days)	11.9 N/cm
• PE (after 14 days)	5.7 N/cm	• Steel (initial)	12 N/cm
• PET (initial)	9.3 N/cm	• Steel (after 14 days)	13.4 N/cm

Additional Information

According to VDA278 analysis, tesa 4967 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=4967>