


# tesa® 88210

## Optically Clear Adhesive



### Product Information

250µm Optically Clear Adhesive for Automotive Applications

### Product Description

tesa® OCA 88210 is a 250µm thick, automotive grade, highly transparent acrylic tape made in clean rooms for optically clear lamination, ideal for large and curved automotive displays. The 88210 exhibits anti-mura performance, while maintaining balanced optical performance, reliability, adhesion and other performance aspects.

Product consists of transparent double PET liners, separately in 75µm and 100µm thickness.

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                  |             |                                    |        |
|------------------|-------------|------------------------------------|--------|
| • Type of liner  | PET         | • Thickness of easy release liner  | 75 µm  |
| • Color          | transparent | • Thickness of tape                | 250 µm |
| • Color of liner | transparent | • Thickness of tight release liner | 100 µm |

### Product Assortment

- |                         |         |                    |             |
|-------------------------|---------|--------------------|-------------|
| • Available thicknesses | 0.25 mm | • Available colors | transparent |
|-------------------------|---------|--------------------|-------------|

### Properties/Performance Values

- |                             |           |                               |        |
|-----------------------------|-----------|-------------------------------|--------|
| • Haze                      | 0.1 %     | • Release of liner - outside  | easy   |
| • Humidity resistance       | very good | • Tack                        | good   |
| • Refractive index          | 1.48      | • Temperature resistance max. | 105 °C |
| • Release of liner - inside | tight     | • Temperature resistance min. | -40 °C |

### Adhesion to Values

- |                                     |           |
|-------------------------------------|-----------|
| • Glass (covered side, after 1 day) | 14.7 N/cm |
|-------------------------------------|-----------|

# tesa® 88210

## Optically Clear Adhesive

### Product Information

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=88210>