


tesa® 62141PV40

Product Information



30µm double sided translucent non-woven tape

Product Description

tesa® 62141 is double-sided, translucent non-woven tape, consists of tackified acrylic adhesive and glassine liner, which provides very good bonding strength for FPC mounting applications during the reflow process.

Product Features

- Very good bonding strength before and even after solder reflow process
- Quick bonding performance
- Excellent temperature resistance up to 260°C
- Excellent die-cutting properties
- High conformability for uneven surfaces
- Good converting properties

Application Fields

FPC mounting application of electronic components, subjected to high temperature processing and operating environments.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------------|
| • Backing | non-woven | • Total thickness | 30 µm |
| • Type of adhesive | tackified acrylic | • Color | translucent |
| • Type of liner | glassine | | |

Properties/Performance Values

- | | | | |
|-----------------------------------|------|--------|-----------|
| • Static shear resistance at 23°C | good | • Tack | very good |
|-----------------------------------|------|--------|-----------|

Adhesion to Values

- | | | | |
|----------------------|----------|-------------------------|----------|
| • PI (initial) | 6.8 N/cm | • Steel (initial) | 6.8 N/cm |
| • PI (after 14 days) | 7.1 N/cm | • Steel (after 14 days) | 7.6 N/cm |

tesa® 62141PV40

Product Information

Additional Information

The Adhesion data is tested according to ASTM-3330

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62141PV40>