

Product Information

400µm double sided black reinforced foam tape

tesa® 62948 is a black double sided thin PE foam tape with a PET film reinforcement. The tape is equipped with a tackified acrylic adhesive.

tesa® 62948 features:

- Thickness: 400µm
- Very high bonding strength
- Highly conformable foam backing compensates design tolerances or uneven surfaces
- Excellent sealing function versus humidity and dust
- Dampening properties offer good shock absorption
- Easy converting and handling due to PET reinforcement
- Very good humidity resistance
- Black color for easy detection or design purposes

Main Application

- Touch panel / lens mounting in mobile phones
- Speaker module mounting
- Front panel mounting in notebooks
- Mounting on uneven surfaces

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Technical Data

• Backing material	PE foam	• Tensile strength	27 N/cm
• Color	black	• Type of liner	glassine
• Total thickness	400 µm	• Color of liner	brown
• Type of adhesive	tackified acrylic	• Thickness of liner	71 µm
• Elongation at break	50 %	• Weight of liner	80 g/m ²

Adhesion to

• Steel (initial)	5.8 N/cm	• Steel (after 14 days)	13.1 N/cm
• ABS (initial)	5.8 N/cm	• ABS (after 14 days)	9.0 N/cm
• Aluminium (initial)	4.9 N/cm	• Aluminium (after 14 days)	10.8 N/cm
• Glass (initial)	7.3 N/cm	• Glass (after 14 days)	10.1 N/cm
• PC (initial)	6.9 N/cm	• PC (after 14 days)	10.8 N/cm
• PE (initial)	2.3 N/cm	• PE (after 14 days)	2.3 N/cm
• PET (initial)	4.9 N/cm	• PET (after 14 days)	7.3 N/cm
• PVC (initial)	6.0 N/cm	• PVC (after 14 days)	13.2 N/cm

tesa® 62948



Product Information

Properties

- | | | | |
|--------------------------|------|-----------------------------------|------|
| • Tack | ●● | • Softener resistance | ●● |
| • Ageing resistance (UV) | ●●●● | • Static shear resistance at 23°C | ●●●● |
| • Humidity resistance | ●●●● | • Static shear resistance at 40°C | ●●●● |

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

Additional Information

Peel adhesion data based on 90° test method.

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit
<http://l.tesa.com/?ip=62948>