



tesa® 4900

Product Information



Acrylic transfer tape

Product Description

tesa® 4900 consists of a transparent pure acrylic adhesive.

Product Features

- The adhesive is transparent, ageing resistant and has a high initial tack.
- tesa® 4900 also withstands elevated temperatures.

Application Fields

- Splicing of paper and filmic webs, particularly flying splices
- Mounting of displays and posters

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Type of liner	glassine	• Type of adhesive	acrylic
• Weight of liner	80 g/m ²	• Color of liner	brown
• Backing material	none	• Thickness of liner	71 µm

Properties/Performance Values

• Ageing resistance (UV)	very good	• Static shear resistance at 40°C	medium
• Chemical resistance	very good	• Tack	very good
• Humidity resistance	good	• Temperature resistance long term	80 °C
• Softener resistance	medium	• Temperature resistance short term	200 °C
• Static shear resistance at 23°C	medium		



tesa[®] 4900

Product Information

Adhesion to Values

• ABS (initial)	2.9 N/cm	• PET (after 14 days)	3.7 N/cm
• ABS (after 14 days)	4.6 N/cm	• PP (initial)	1.3 N/cm
• Aluminium (initial)	2.7 N/cm	• PP (after 14 days)	2.6 N/cm
• Aluminium (after 14 days)	3.1 N/cm	• PS (initial)	3.1 N/cm
• PC (initial)	3.1 N/cm	• PS (after 14 days)	3.8 N/cm
• PC (after 14 days)	5 N/cm	• PVC (initial)	2.7 N/cm
• PE (initial)	0.8 N/cm	• PVC (after 14 days)	5.6 N/cm
• PE (after 14 days)	1 N/cm	• Steel (initial)	3.4 N/cm
• PET (initial)	2.4 N/cm	• Steel (after 14 days)	3.8 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=04900>