



tesa® 60150 Adhesion Promoter Universal



Información Producto

Promotor adhesivo estándar

Descripción del producto

tesa® 60150 promotor de adhesión, se utiliza para mejorar la adherencia de las cintas tesa® ACX^{plus} a diferentes clases de sustratos, tesa® 60150 Promotor de adhesión debe ser probado antes de su primer uso.

Características

- It is especially recommended for our tesa® ACX^{plus} product family
- The UV-traceability of our tesa® 60150 Adhesion Promoter allows easy quality control during the application process

Aplicación

Our tesa® 60150 Adhesion Promoter is recommended for several substrates such as PVC, PP/EPDM, ABS, zinc, steel or aluminum. The compatibility with other surfaces should always be tested accordingly. This product can be used to significantly improve the bonding strength of tesa® ACX^{plus} tapes. Testing shows significantly higher peel adhesion values.

Información Técnica: (valores promedio)

Los valores en esta sección son considerados solamente como representativos o típicos y no deben usarse para propósitos específicos.

Composición del producto

- Color amarillo claro

Propiedades / Valores de rendimiento

- | | | | |
|---------------------------|------------------------|--------------|----------|
| • Consistencia | líquido | • Sólidos | 7 % |
| • Densidad | 0.81 g/cm ³ | • Viscosidad | 15 mPa s |
| • Ratio de dispersión ca. | 15 m ² /l | | |

Información adicional

Before using our adhesion promoter, the bonding surface should be free of dust, grease, oil, moisture, and other contaminants. Therefore, we highly recommend cleaning the substrate with a lint-free cloth using solvents, such as ethanol or isopropanol alcohol or our tesa® 60040 Industry Cleaner.

Once the surface has been cleaned, you can go ahead and apply our tesa® 60150 Adhesion Promoter. We recommend applying our adhesion promoters with a melamin sponge or lint-free cloth. The entire surface should be coated thinly with adhesion promoter in order to reach the highest bonding performance. It is important to wait at least 30 seconds and up to 5 minutes (depending on ambient temperature and humidity) in order to give solvents time to evaporate. Please make sure to keep the prepared surface free of contaminants prior to applying the tape.

Para más información sobre este producto, por favor visite la página
<http://l.tesa.com/?ip=60150>



tesa[®] 60150

Adhesion Promoter Universal

Información Producto

Información adicional

Once the substrate has been properly pre-treated with tesa[®] 60150 Adhesion Promoter, the bond should be established within several hours. Please note that due to the multitude of available substrate formulations in the marketplace, it is recommended to test our tesa[®] Adhesion Promoter prior to usage.

- The shelf life of this product amounts to at least 12 months when stored at room temperature in its sealed original container.
- For further information and advice on safe handling please refer to our safety data sheet (SDS), which is available upon request.

Disclaimer

Los productos de tesa[®] demuestran su calidad en el día a día en condiciones exigentes y son sujetas a estrictos controles. Toda la información y datos técnicos arriba mencionados son suministrados en base a nuestro conocimiento y nuestra experiencia. Deberían ser considerados como valores promedios y no apropiados para una homologación. Por lo tanto tesa SE no puede dar garantías, explícita o implícitamente, incluyendo pero no limitando a cualquier garantía de comercialización o adecuación para un fin en particular. El usuario es responsable de determinar si los productos de tesa[®] son adecuados para una aplicación en particular y funcionan con los equipos de aplicación que tenga. En caso de duda, nuestro equipo técnico estará encantado de poder ayudarle.



Para más información sobre este producto, por favor visite la página
<http://l.tesa.com/?ip=60150>