



tesa[®] 68614 Asia

Product Information

100µm double sided translucent non-woven tape

Deskripsi Produk

tesa[®] 68614 is a translucent, double-sided self-adhesive tape consisting of a non-woven backing and a tackified acrylic adhesive.

tesa[®] 68614 features especially:

- High bonding strength on various kinds of substrates
- Good temperature resistance performance

Penerapan

- General purpose mounting applications

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Konstruksi Produk

- | | | | |
|-----------------|-------------------|-------------------|-------------|
| • Penyangga | non-woven | • Ketebalan total | 100 µm |
| • Jenis perekat | tackified acrylic | • Warna | translucent |
| • Jenis liner | PE-coated paper | | |

Properti / Nilai Kinerja

- | | | | |
|--|--------|--|-----------|
| • Ageing resistance (UV) | good | • Ketahanan terhadap geser statis pada 23 °C | very good |
| • Durasi ketahanan suhu jangka panjang | 70 °C | • Ketahanan terhadap geser statis pada 70 °C | good |
| • Durasi ketahanan suhu jangka pendek | 150 °C | • Ketahanan terhadap kelembapan | good |
| • Ketahanan terhadap bahan kimia | medium | • Paku payung | good |





tesa[®] 68614

Asia

Product Information

Adhesion to Values

• Daya rekat ke ABS (awal)	7.5 N/cm	• Daya rekat ke PET (setelah 14 hari)	7.7 N/cm
• Daya rekat ke ABS (setelah 14 hari)	9.3 N/cm	• Daya rekat ke PP (awal)	5.9 N/cm
• Daya rekat ke PC (awal)	7.7 N/cm	• Daya rekat ke PP (setelah 14 hari)	7.3 N/cm
• Daya rekat ke PC (setelah 14 hari)	7.1 N/cm	• Daya rekat ke PVC (awal)	6 N/cm
• Daya rekat ke PE (awal)	4.4 N/cm	• Daya rekat ke PVC (setelah 14 hari)	9 N/cm
• Daya rekat ke PE (setelah 14 hari)	5.6 N/cm	• Daya rekat ke Baja (awal)	6 N/cm
• Daya rekat ke PET (awal)	7.5 N/cm	• Daya rekat ke Baja (setelah 14 hari)	10 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=68614>