



# tesa® 88642

## Product Information



120µm double coated tissue tape

### Deskripsi Produk

tesa® 88642 is a 120µm double coated tissue tape consisting of a tissue backing and a tackified acrylic adhesive.

### Product Features

- Good adhesion to a variety of polar surfaces
- Sufficient adhesion to non-polar surfaces
- Excellent holding power at escalated temperature
- Easily removable liner
- Suitable for permanent applications

### Penerapan

- Name plate mounting
- Control panel mounting
- Foam lamination
- Textile lamination

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Konstruksi Produk

- |                   |                   |                   |                 |
|-------------------|-------------------|-------------------|-----------------|
| • Penyangga       | non-woven         | • Warna           | translucent     |
| • Jenis perekat   | tackified acrylic | • Ketebalan liner | 130 µm          |
| • Jenis liner     | PE-coated paper   | • Warna liner     | white/blue logo |
| • Ketebalan total | 120 µm            |                   |                 |

### Properti / Nilai Kinerja

- |  |        |  |           |
|--|--------|--|-----------|
| • Durasi ketahanan suhu jangka panjang | 70 °C  | • Ketahanan terhadap geser statis pada 70 °C | very good |
| • Durasi ketahanan suhu jangka pendek  | 160 °C | • Paku payung                                | good      |



# tesa® 88642

## Product Information

### Adhesion to Values

• Daya rekat ke ABS (awal)	8.5 N/cm	• Daya rekat ke PE (setelah 3 hari)	5 N/cm
• Daya rekat ke ABS (setelah 3 hari)	10.2 N/cm	• Daya rekat ke PET (awal)	6.7 N/cm
• Daya rekat ke Kaca (awal)	7.5 N/cm	• Daya rekat ke PP (awal)	5.8 N/cm
• Daya rekat ke Kaca (setelah 3 hari)	9.5 N/cm	• Daya rekat ke PP (setelah 3 hari)	7 N/cm
• Daya rekat ke PC (awal)	9.1 N/cm	• Daya rekat ke PVC (awal)	6.5 N/cm
• Daya rekat ke PC (setelah 3 hari)	11.7 N/cm	• Daya rekat ke Baja (awal)	7.5 N/cm
• Daya rekat ke PE (awal)	4.4 N/cm	• Daya rekat ke Baja (setelah 3 hari)	10.1 N/cm

### Additional Information

The Adhesion to Steel data is tested according to ASTM-3330

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=88642>