



tesa® 88661

Product Information



50µm double coated PET tape

Deskripsi Produk

tesa® 88661 is a transparent, double coated self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive. it is the ideal solution for multi-purpose mounting applications specifically in general industry market and is extremely converting friendly.

Product Features

- Good initial tack and adhesion to a wide variety surfaces
- Medium shear strength
- Excellent temperature resistance
- Wrinkle resistant PE-coated liner

Penerapan

- Name plate mounting
- Membrane switch mounting
- Foam lamination
- Light strips mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Konstruksi Produk

- | | | | |
|-------------------|-------------------|---------------|----------------------|
| • Penyangga | PET | • Warna | transparent |
| • Jenis perekat | tackified acrylic | • Berat liner | 128 g/m ² |
| • Jenis liner | PE-coated paper | • Warna liner | white/blue logo |
| • Ketebalan total | 50 µm | | |

Properti / Nilai Kinerja

- | | | | |
|--|---------|--|--------|
| • Perpanjangan saat putus | 50 % | • Ketahanan terhadap geser statis pada 23 °C | medium |
| • Kekuatan tarik | 20 N/cm | • Ketahanan terhadap geser statis pada 70 °C | medium |
| • Durasi ketahanan suhu jangka panjang | 100 °C | • Paku payung | good |
| • Durasi ketahanan suhu jangka pendek | 200 °C | | |



tesa® 88661

Product Information

Adhesion to Values

• Daya rekat ke ABS (awal)	5.1 N/cm	• Daya rekat ke PET (awal)	5.2 N/cm
• Daya rekat ke ABS (setelah 14 hari)	6.2 N/cm	• Daya rekat ke PET (setelah 14 hari)	6 N/cm
• Daya rekat ke PC (awal)	5.6 N/cm	• Daya rekat ke PP (awal)	2 N/cm
• Daya rekat ke PC (setelah 14 hari)	6.6 N/cm	• Daya rekat ke PP (setelah 14 hari)	5.5 N/cm
• Daya rekat ke PE (awal)	2 N/cm	• Daya rekat ke Baja (awal)	5.5 N/cm
• Daya rekat ke PE (setelah 14 hari)	3.1 N/cm	• Daya rekat ke Baja (setelah 14 hari)	7.2 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=88661>