


tesa® 8853

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Konstruksi Produk

• Penyangga	ultra thin non-woven	• Ketebalan total	50 µm
• Jenis perekat	tackified acrylic	• Warna	translucent
• Jenis liner	glassine	• Warna liner	white

Berbagai macam produk

• Warna yang tersedia	translucent
-----------------------	-------------

Properti / Nilai Kinerja

• Ageing resistance (UV)	sangat bagus	• Ketahanan terhadap kelembapan	sangat bagus
• Ketahanan terhadap bahan kimia	bagus		

Adhesion to Values

• Daya rekat ke ABS (awal)	4.8 N/cm	• Daya rekat ke PET (awal)	5 N/cm
• Daya rekat ke ABS (setelah 14 hari)	6 N/cm	• Daya rekat ke PET (setelah 14 hari)	5.4 N/cm
• Daya rekat ke Aluminium (awal)	4.5 N/cm	• Daya rekat ke PI (awal)	5.9 N/cm
• Daya rekat ke Aluminium (setelah 14 hari)	5.9 N/cm	• Daya rekat ke PI (setelah 14 hari)	6 N/cm
• Daya rekat ke PC (awal)	5.8 N/cm	• Daya rekat ke Baja (awal)	5.3 N/cm
• Daya rekat ke PC (setelah 14 hari)	6.9 N/cm	• Daya rekat ke Baja (setelah 14 hari)	6.5 N/cm

tesa® 8853

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=8853PV40>