

tesa® 50565

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Konstruksi Produk

• Penyangga	aluminium foil	• Ketebalan liner	65 µm
• Jenis perekat	acrylic	• Ketebalan pita	_NULL µm
• Jenis liner	paper	• Warna liner	white
• Ketebalan total	90 µm		

Properti / Nilai Kinerja

• Perpanjangan saat putus	8 %	• Kemampuan disobek dengan tangan	bagus
• Kekuatan tarik	35 N/cm	• Suhu operasi dari	-40 °C
• Backing appearance (visual)	reflective	• Suhu operasi sampai	160 °C

Adhesion to Values

• Daya rekat ke Baja	6 N/cm
----------------------	--------

Sertifikat

Sertifikat sesuai dengan

- UL 510

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=50565>