

tesa® 4316

Product Information



Berkelanjutan Aspek

54% bio-based content in total product excluding liner (by weight)



Untuk informasi lebih lanjut: <https://www.tesa.com/product-sustainability>

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Konstruksi Produk

• Penyangga	slightly-creped paper	• Berbasis Bio (berdasarkan berat)	54 %
• Jenis perekat	natural rubber	• Ketebalan total	140 µm

Properti / Nilai Kinerja

• Perpanjangan saat putus	10 %	• Ketahanan suhu (30 menit)	120 °C
• Kekuatan tarik	38 N/cm	• Mudah dilepas	yes
• Kemampuan disobek dengan tangan	sangat bagus	• Temperature resistance (60 min)	100 °C

Adhesion to Values

• Daya rekat ke Baja	3.4 N/cm
----------------------	----------

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=4316>