productinformation

tesa[®] 4976 Double-sided PU-foam tape

tesa[®] 4976 is a double-sided tape consisting of a conformable black open cell PU-foam backing and a tackified acrylic adhesive.

tesa® 4976 features especially:

- Good compensation for design tolerances
- Level out different thermal elongation of materials
- Shock absorption and sealing function
- High short term temperature resistance

Main Application

Fixing of mirrors, decorative profiles and signs

Mounting of cable channels

Technical Data

 Backing material	PU foam	Tensile strength	6.66 N/cm
Color	black	Type of liner	glassine
Total thickness	540 μm	Colour of liner	brown
Type of adhesive	tackified acrylic	Thickness of liner	70 μm
Elongation at break	250 %	Weight of liner	80 g/m²

Adhesion to

:	Steel (initial) ABS (initial)	10.0 N/cm 7.0 N/cm	Steel (after 14 days) ABS (after 14 days)	12.0 N/cm 12.0 N/cm	
	Aluminium (initial)	5.0 N/cm	Aluminium (after 14 da	-	
	PC (initial)	8.0 N/cm	PC (after 14 days)	12.0 N/cm	
	PE (initial)	4.1 N/cm	PE (after 14 days)	4.3 N/cm	I
	PET (initial)	5.5 N/cm	PET (after 14 days)	10.0 N/cm	I
	PP (initial)	3.7 N/cm	PP (after 14 days)	7.4 N/cm	1
	PS (initial)	5.0 N/cm	PS (after 14 days)	10.0 N/cm	1
	PVC (initial)	5.5 N/cm	PVC (after 14 days)	12.0 N/cm	1

For latest information on this product please visit <u>http://l.tesa.com/?ip=04976</u>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



great to work with

tesa[®] 4976 Double-sided PU-foam tape

Properties										
 Temperature resistance short term Temperature resistance long term Tack Ageing resistance (UV) Humidity resistance 	200 °C 80 °C • • •	 Resistance to chemicals Softener resistance Static shear resistance at 23°C Static shear resistance at 40°C 	••							
Evaluation across relevant tesa [®] assortment: •••• very good ••• good •• medium • low										

Additional Information

Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

For latest information on this product please visit http://l.tesa.com/?ip=04976

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

