

tesa® 61395

200µm double sided black high performance filmic tape

tesa® 61395 is a black, double sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 200µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

Main Application

- Lens mounting in mobile phones
- Touch panel mounting

Technical Data

| | | | |
|-----------------------|-------------------|----------------------|----------------------|
| ▪ Backing material | PET film | ▪ Tensile strength | 20 N/cm |
| ▪ Color | black | ▪ Type of liner | glassine |
| ▪ Total thickness | 200 µm | ▪ Colour of liner | white with tesa logo |
| ▪ Type of adhesive | tackified acrylic | ▪ Thickness of liner | 71 µm |
| ▪ Elongation at break | 50 % | ▪ Weight of liner | 80 g/m ² |

Adhesion to

| | | | |
|-------------------|-----------|-------------------------|-----------|
| ▪ Steel (initial) | 13.0 N/cm | ▪ Steel (after 14 days) | 15.8 N/cm |
| ▪ ABS (initial) | 10.0 N/cm | ▪ ABS (after 14 days) | 13.3 N/cm |
| ▪ Glass (initial) | 14.3 N/cm | ▪ Glass (after 14 days) | 16.6 N/cm |
| ▪ PC (initial) | 11.6 N/cm | ▪ PC (after 14 days) | 19.5 N/cm |
| ▪ PMMA (initial) | 14.2 N/cm | ▪ PMMA (after 14 days) | 19.2 N/cm |

Properties

| | | | |
|-------------------------------------|--------|-----------------------------------|------|
| ▪ Temperature resistance short term | 200 °C | ▪ Humidity resistance | ●●●● |
| ▪ Temperature resistance long term | 100 °C | ▪ Static shear resistance at 23°C | ●●● |
| ▪ Tack | ●● | ▪ Static shear resistance at 40°C | ●●● |
| ▪ Ageing resistance (UV) | ●●●● | | |

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

For latest information on this product please visit <http://l.tesa.com/?ip=61395>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.