# productinformation

# tesa® 62510

# Double sided PE foam mounting tape

tesa® 62510 is a double sided PE foam tape for mounting applications. It consists of a highly conformable PE-foam backing and a tackified acrylic adhesive.

#### Product benefits:

\*High ultimate adhesion level for a reliable bonding performance

- Fully outdoor suitable: UV, water and ageing resistant
- Conformable PE foam core with high inner strength
- Suitable for automatic and manual module assembly
- Easy solar module assembly due to a high foam compression rate

## Main Application

General mounting applications Mounting of trims and profiles Solar module frames

### Technical Data

•	Backing material	PE foam •	•	Type of adhesive	tackified acrylic
•	Color	black/white •		Elongation at break	180 %
•	Total thickness	1000 μm	•	Tensile strength	10 N/cm

## Adhesion to

•	Steel (initial)	13.5 N/cm	•	Steel (after 14 days)	13.5 N/cm
٠	ABS (initial)	8.0 N/cm		ABS (after 14 days)	13.5 N/cm
٠	Aluminium (initial)	8.0 N/cm		Aluminium (after 14 days)	13.5 N/cm
٠	PC (initial)	8.0 N/cm		PC (after 14 days)	13.5 N/cm
•	PE (initial)	0.9 N/cm	•	PE (after 14 days)	0.9 N/cm
٠	PET (initial)	6.0 N/cm		PET (after 14 days)	13.5 N/cm
٠	PP (initial)	1.2 N/cm		PP (after 14 days)	1.2 N/cm
٠	PS (initial)	8.0 N/cm		PS (after 14 days)	8.0 N/cm
•	PVC (initial)	13.5 N/cm		PVC (after 14 days)	13.5 N/cm

For latest information on this product please visit <a href="http://l.tesa.com/?ip=62510">http://l.tesa.com/?ip=62510</a>

## tesa® 62510

## Double sided PE foam mounting tape

## **Properties**

- Temperature resistance short term
- Temperature resistance long term
- Tack
- Ageing resistance (UV)
- Humidity resistance

- 80 °C Softener resistance
  - Static shear resistance at 23°C
  - Static shear resistance at 40°C
  - Static shear resistance at 70°C



Evaluation across relevant tesa® assortment: ••• very good •• good • medium • lov

#### Additional Information

Liner variants:

PV0 brown glassine paper (70μm) PV13 transparent PET (50μm) PV15 blue PE (100μm)

Peel Adhesion:

-immediately: foam splitting on steel

-after 14 days: foam splitting on steel, ABS, Aluminum, PC, PET, PS, PVC

tesa® 62510 is recognized by UL as photovoltaic polymeric material (QIHE2).

tesa® 62510 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 climate tests and a 85°C temperature resistance.

The temperature resistance (short/long) of tesa® 62510 has been approved according to tesa test method under static load.